

JW Plus Series **Namic1.0**

n-Type Bifacial Dual-Glass Module

JW-HD132N2-R2 615-640W

Maximum Power Output **640W** Maximum Module Efficiency **23.7%** Power Output Tolerance **0~+3%**

Namic Technology



Better Customer Value

- Lower 1st-year degradation (1%) and annual degradation (0.4%)
- Higher module efficiency, reduced BOS & LCOE, and increased ROI



Enhanced Energy Yield

- Excellent IAM performance and better low-light performance
- Better temperature coefficient (-0.28%/°C) and lower operating temperature resulting in increased energy yield



Robust Reliability

- Engineered with Nano-Armor layer for superior resistance to PID degradation and UV attenuation
- Innovative non-destructive cutting tech to minimize microcrack risks
- Exceptional environmental resilience against salt mist, ammonia, PID, sandstorms, and high-temperature/humidity conditions



High Safety

- Namic technology enhances hot-spot resistance
- Rigorously tested for mechanical load: 5,400Pa front load & 2,400Pa rear load




Munich RE   



IEC 61215(2021)/IEC 61730(2023)/IEC 61701/IEC 62716
ISO 9001:2015: Quality Management System
ISO 14001:2015: Environment Management System
ISO 45001:2018: Occupational health and safety
IEC 62941:2019: Quality system for PV module manufacturing

Linear Performance Warranty



12 Years Product Material & Workmanship 30 Years Linear Performance Warranty

Version 2026.05 ©Jolywood (Taizhou) Solar Technology Co., Ltd. All rights reserved.

Add: No.6 Kaiyang Rd., Jiangyan Economic Development Zone, Taizhou, Jiangsu Province, China, 225500

TEL: +86 523 80612799

Email: info@jolywood.cn

www.jolywood.com



@Jolywood Solar

JW-HD132N2 | n-type Bifacial Dual-Glass Module

Electrical Properties | STC*

Testing Condition	Front Side	Front Side	Front Side	Front Side	Front Side	Front Side
Peak Power (P _{max}) (W)	615	620	625	630	635	640
MPP Voltage (V _{mp}) (V)	41.09	41.27	41.45	41.63	41.24	41.40
MPP Current (I _{mp}) (A)	14.97	15.02	15.08	15.13	15.40	15.46
Open Circuit Voltage (V _{oc}) (V)	47.86	48.06	49.19	49.30	49.50	49.70
Short Circuit Current (I _{sc}) (A)	15.82	15.87	16.05	16.15	16.31	16.37
Module Efficiency (%)	22.8	23.0	23.1	23.3	23.5	23.7

*STC: Irradiance 1000 W/m², Cell Temperature 25°C, AM1.5
The data above is for reference only and the actual data is in accordance with the practical testing
Power Measurement Tolerance ±3%

Electrical Properties | NMOT*

Testing Condition	Front Side	Front Side	Front Side	Front Side	Front Side	Front Side
Peak Power (P _{max}) (W)	461	464	468	472	476	479
MPP Voltage (V _{mp}) (V)	39.34	39.51	39.69	39.86	39.49	39.64
MPP Current (I _{mp}) (A)	11.71	11.75	11.80	11.84	12.04	12.09
Open Circuit Voltage (V _{oc}) (V)	45.82	46.01	47.10	47.20	47.40	47.59
Short Circuit Current (I _{sc}) (A)	12.78	12.82	12.96	13.04	13.17	13.22

*NMOT: Irradiance 800 W/m², Ambient Temperature 20°C, Wind Speed 1 m/s

Electrical Properties Under Different Rear Gain | JW-HD132N2-R2-640

Power Gain (%)	Peak Power (P _{max}) (W)	MPP Voltage (V _{mp}) (V)	MPP Current (I _{mp}) (A)	Open Circuit Voltage (V _{oc}) (V)	Short Circuit Current (I _{sc}) (A)
10	704.0	41.40	17.00	49.70	18.01
15	736.0	41.40	17.78	49.70	18.82
20	768.0	41.50	18.51	49.80	19.60
25	800.0	41.50	19.28	49.80	20.42
30	832.0	41.50	20.05	49.80	21.24

Operating Properties

Operating Temperature	-40°C ~ +85°C
Maximum System Voltage	1500V (IEC)
Maximum Series Fuse Rating	35A
Bifaciality*	70%

Static Load Front side 5400Pa, Rear side 2400Pa

*Bifaciality = P_{max}rear (STC) / P_{max}front (STC) , Bifaciality tolerance: ±5%

Temperature Coefficient


Temperature Coefficient of P _{max}	-0.280%/°C
Temperature Coefficient of V _{oc}	-0.250%/°C
Temperature Coefficient of I _{sc}	+0.045%/°C
Nominal Operating Cell Temperature	45±2°C

Specification


Number of Cells	132pcs
Module Dimension	2382mm*1134mm*30mm
Weight	32.6kg
Front / Rear Glass*	2.0mm*2.0mm Heat-strengthened glass
Frame	Anodized Aluminium Alloy
Junction Box	IP68 (3 diodes)
Length of Cable	4.0mm ² , +300mm/-180mm (Cable length can be customized)
Packaging Configuration	36pcs/Pallet, 720pcs/40HQ Container

*The specification and key features described in this datasheet may deviate slightly and are not guaranteed. Due to ongoing innovation, R&D enhancement, Jolywood (Taizhou) Solar Technology Co., Ltd. reserves the right to make any adjustment to the information described herein at any time without notice. Please always obtain the most recent version of the datasheet which shall be duly incorporated into the binding contract made by the parties governing all transactions related to the purchase and sale of the products described herein.


Engineering Drawing (unit: mm)



Characteristic Curves | JW-HD132N2-R2-640



I-V Characteristics At Different Irradiations



P-V Characteristics At Different Irradiations



Add: No.6 Kaiyang Rd., Jiangyan Economic Development Zone,
Taizhou, Jiangsu Province, China, 225500

TEL: +86 523 80612799

Email: info@jolywood.cn

www.jolywood.com

